

**Henkel**

**Surface  
Technologies**

**HENKEL Australia Pty Ltd**  
A.C.N. 001 302 996

135-141 Canterbury Road  
KILSYTH VICTORIA 3164

Tel: (03) 9728 7200  
Fax: (03) 9728 5877  
Customer Service 1 300 736 777

**Distributed by**  
**Solvents Australia Pty Ltd**  
ABN 74 003 523 117  
77 Bassett Street  
Mona Vale NSW 2100  
PO Box 928 Mona Vale NSW 1660  
Tel: (02)9979 6866  
Fax: (02)9979 6864

## TECHNICAL DATA BULLETIN

# ALODINE 1200L/1000L

## (Manual Operation)

### A. SUMMARY

#### 1. INTRODUCTION

Alodine\* 1000L & 1200L are liquid chemicals, designed to produce protective and paint bonding coatings on aluminium and aluminium alloys.

Alodine 1000L produces colourless coatings and is used for sign writing or the application of clear finishes. For other applications, Alodine 1200L, which produces golden to tan coatings, should be used.

Alodine 1000L & 1200L are made specifically for manual application. Other versions of Alodine 1200 are available for application by immersion or recirculation spray.

These coatings conform to U.S.A. Military Specification MIL-C-5541E. The Alodine 1000L & 1200L coatings are electrically conductive. Fresh coatings (obtained from two minutes contact with deoxidised surfaces) usually have a resistance of 170 micro-ohms (i.e. a conductivity of 6,000 siemens) and this increases with age.

#### 2. MAKE UP AND OPERATION

Alodine 1000L & 1200L are used without dilution, and are applied by brush, synthetic sponge or mop to the clean substrate.

One litre will treat approximately 10 square metres of surface.

#### 3. EQUIPMENT

Containers should be of plastic or similar acid proof material. Do not use tin cans, galvanised buckets or glass containers.

**B. TECHNICAL DETAILS:****1. OPERATIONAL RECOMMENDATIONS****(a) Pre Cleaning**

Remove oil and grease deposits with a detergent solution, mineral turps, white spirits or kerosene. Wipe dry with a clean cloth. If no corrosion is evident, proceed with the application of the chemical, but first wet the surface with water.

If corrosion is evident, or if the surface requires to be deoxidised, apply **Deoxidine\* 624** diluted, one (1) volume with three (3) volumes of water, or undiluted until the surface is free of water breaks. Flush off with fresh water or wipe up the chemical residues with clean rags. There is no need to dry the surface completely; in fact a wet surface will assist the formation of a uniform coating.

**(b) Application**

Apply the undiluted **Alodine 1000L** or **Alodine 1200L** solution freely using nylon or bristle brushes, synthetic sponge, cotton mops, or clean cloths; moving over a convenient area for about 1-2 minutes, or until the surface is uniformly wet. Apply a fresh lot of **Alodine** solution and leave for no more than 30 seconds. Hose off the residual chemical, and blow out any crevices, joints or pools.

For vertical surfaces, start at the bottom and treat each section fully before moving up to the next section. Finally, hose the complete article. Allow the article to air dry completely, or force dry at a temperature not exceeding 82°C (180°F) before applying further coatings.

**2. PLANT MAINTENANCE**

Application equipment, spills, etc. should be flushed with water to prevent the drying of residues.

Water authorities commonly set limits on the level of chromic acid in effluent. Where applicable, **Alodine** wastes and rinsings need to be treated before discharge into a sewerage system. Your Henkel\*\* Technical Representative can provide basic recommendations on this step.

**3. HANDLING PRECAUTIONS**

**4. SPECIFICATIONS**

Alodine 1000L & 1200L are approved for use under MIL-C-5541E. Class 1A Form III Method B application for Alodine 1200L and Class 3 Form 1 Method A&C for Alodine 1000L.

**5. HENKEL\* REFERENCE**

Alodine 1000L  
Alodine 1200L

- \* Registered Trade Mark of Parker Amchem U.S.A.
- \*\* Registered Trade Mark of Henkel Australia Pty. Limited

**DISCLAIMER**

Any information given is, to the best of our knowledge, the best currently available, with respect to our products and their use, but it is subject to revision as additional knowledge and experience is gained. Such information is offered as a guideline for experimentation only and is not to be construed as a representation that the material is suitable for any particular purpose or use. Customers are encouraged to make their own enquiries as to the material's characteristics and, where appropriate, to conduct their own tests in the specific context of the material's intended use. This information is not a license to operate under nor is it intended to suggest infringement of any patent. We guarantee a uniform quality standard for this product. The only conditions and warranties accepted by Henkel in relation to this product or process are those implied by either Commonwealth or State statutes.